



Steel Wire Rope 6x24-7FC

Product information



Rope construction: 6x24-7FC.

Marking: According to standard

Standard: EN 12385-4

Fill factor: 0.41

Slings



Part code	Rope diameter mm	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
101100604250310	6	1,770	Galvanized	sZ	17.9	11.6	Dry	11
101100804250310	8	1,770	Galvanized	sZ	31.8	20.6	Dry	20
101101004250310	10	1,770	Galvanized	sZ	49.6	32.2	Dry	32
101101204250310	12	1,770	Galvanized	sZ	71.4	46.4	Dry	46
101101404250310	14	1,770	Galvanized	sZ	97.2	63.1	Dry	62
101101604250310	16	1,770	Galvanized	sZ	127	82.4	Dry	81
101101804250310	18	1,770	Galvanized	sZ	161	104	Dry	103
101102004250310	20	1,770	Galvanized	sZ	198	129	Dry	127
101102204250310	22	1,770	Galvanized	sZ	240	156	Dry	154